

HYPAFLEX™ CSPE

When it comes to long-term performance in exposed liner and cover applications, HypaFlex™ (Chlorosulfonated Polyethylene - CSPE) is the gold standard. Engineered to withstand extreme heat and UV exposure, HypaFlex™ has been used extensively for water containment and protection for over 50 years and is backed with an industry-leading 30-year weathering warranty.

The use of HypaFlex™ floating covers in reservoirs is one of the most economical methods of storing and treating large volumes of water. Reservoirs using CSPE are often up to 70% more cost-effective versus above-ground tanks or underground clearwells. With over 400 successful floating cover projects worldwide, you can trust that HypaFlex™ is built to last.

April 2023		HypaFlex™ CSPE			
Style	ASTM	M-283	M-284	M-423	M-529
Total Plies		3	3	3	5
Thickness (Nominal)	D751	36 mil 0.9 mm	45 mil 1.14 mm	60 mil 1.5 mm	60 mil 1.5 mm
Tensile Strength	D751	225 lbs 1000 N	250 lbs 1100 N	300 lbs 1300 N	390 lbs 1700 N
Elongation	D751	50%	60%	75%	30%
Puncture	FTMS101 (2031)	200 lbs 890 N	225 lbs 1000 N	250 lbs 1100 N	400 lbs 1780 N
Ozone Resistance	D1149	No Effect	No Effect	No Effect	No Effect
Hydrostatic Resistance	D751A	300 psi 2100 kPa	350 psi 2400 kPa	400 psi 2760 kPa	500 psi 3450 kPa
Tear Strength	D751 Tongue	70 lbs 310 N	80 lbs 350 N	80 lbs 350 N	130 lbs 580 N
Low Temperature	D2136	-40°F -40°C	-40°F -40°C	-40°F -40°C	-40°F -40°C

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com

HYPAFLEX™ CSPE

April 2023		CSPE Minimum Shop Seam Strengths			
Style	ASTM	M-283	M-284	M-423	M-529
Heat Bonded Seam Strength	D7749	200 lbs 890 N	225 lbs 1000 N	270 lbs 1200 N	360 lbs 1600 N
Heat Bonded Peel Adhesion	D7747	Film Tear Bond	Film Tear Bond	Film Tear Bond	Film Tear Bond

April 2023		CSPE Minimum Field Seam Strengths			
Style	ASTM	M-283	M-284	M-423	M-529
Heat Bonded Seam Strength	D7749	200 lbs 890 N	225 lbs 1000 N	270 lbs 1200 N	360 lbs 1600 N
Heat Bonded Peel Adhesion	D7747	Film Tear Bond	Film Tear Bond	Film Tear Bond	Film Tear Bond

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com