

QUIKGRID™ BIAxIAL COMPOSITE - GEOGRID

Design and build with confidence; we empower you to achieve cost-effective, proven, engineered solutions. Fueled by an innovative spirit, our industry-leading technology solves the toughest soil stabilization, earth reinforcement, and site development challenges.

The composite nature of the QuikGrid™ makes it easy and fast to install and effective in maintaining the separation of imported granular fill from the fines contained in typical saturated base soils.

April 2023		QuikGrid™ BiAxial Composite - Geogrid		
Rev	Test Method	QUIKGRID™ 30		QUIKGRID™ 40
GEOGRID		LBX3030		LBX4040
Raw Material		PP, Black		PP, Black
Tensile Strength, MD/TD	ASTM D6637	30 kN/m/30 kN/m		40 kN/m /40 kN/m
Tensile Strength at 2% Elongation, MD/TD	ASTM D6637	11.0 kN/m /11.0 kN/m		18.0 kN/m /18.0 kN/m
Tensile Strength at 5% Elongation, MD/TD	ASTM D6637	21.0 kN/m /21.0 kN/m		32.0 kN/m /32.0 kN/m
Junction Efficiency ^(1,2) , MD/TD	ASTM D7737/D6637	95%		95%
Flexural Stiffness ⁽³⁾	ASTM D7748	2,000,000 mg-cm		4,800,000 mg-cm
Aperture Size, MD/TD		39 mm x 39 mm		39 mm x 39 mm
GEOTEXTILE		E150	E200	E150
Raw Material		Polyester	Polyester	Polyester
Mass Per Unit Area	ASTM D5261	150 g/m ²	200 g/m ²	150 g/m ²
Tensile Strength MD/TD	ASTM D5035	11 kN/m / 9.5 kN/m	14.5 kN/m / 12 kN/m	11 kN/m / 9.5 kN/m
Elongation at Peak MD/TD	ASTM D5035	50 %	50 %	50 %

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com

Grab Tensile Strength MD/TD	ASTM D4632	740 N / 620 N	1030 N / 850 N	740 N / 620 N
Trapezoidal Tear Strength	MD/TD	300 N / 300 N	365 N / 365 N	300 N / 300 N
Static Puncture Strength (CBR)	ASTM D6241	1800 N	2500 N	1800 N
Apparent Opening Size (AOS)	ASTM D4751	0.23 mm ⁽⁴⁾	0.19 mm ⁽⁴⁾	0.23 mm ⁽⁴⁾
Water Flow Rate		235 l/m ² /Sec	220 l/m ² /Sec	235 l/m ² /Sec
Roll Dimensions (m)		3.95 m x 50 m	3.95 m x 50 m	3.95 m x 50 m

- (1) Expressed as a comparison of ASTM D7737 strength to ASTM D6637 strength of the same sample.
 (2) ASTM D7737 performed at 10% per minute strain rate.
 (3) Using specimens 2 ribs wide with ribs transverse to the specimen cut flush with the exterior edges of the ribs in the direction of the specimen.
 (4) Typical value.

Unless indicated otherwise, values shown are typical roll values based on manufacturers laboratory testing @ 21+/- 1 Degree C

Layfield reserves the right to change this product specification at any time. The user is responsible to verify use/reference of the latest Product Data Sheet

INSTALLATION

The subgrade should be cleared of all vegetation and proof rolled. However, on very soft ground or muskeg, cut vegetation flush with the ground and remove all woody bushes, shrubs and large rocks. The surface of the subgrade should be levelled, and depressions or humps greater than 15 cm (6 in) should be graded out. The biaxial geogrid shall be placed directly on the prepared subgrade. It should be rolled out flat and tight with no folds. Adjacent rolls should be overlapped as a function of subgrade strength and to allow for product continuity once backfilled. For CBR 3.0 and above 20 cm (8 in) to 30 cm (12 in); for CBR 1.0 to 3.0 45 cm (18 in) to 90 cm (36 in) for CBR 1.0 or lower, please contact one of our technical specialists for installation and application recommendations. Care should be taken to ensure that the overlaps are maintained during fill placement. Should a mechanical joint be required then please consult the manufacturer for further details or refer to and follow project specific requirements in the plans, specifications and tender documents.

Disclaimer: Layfield disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

For up-to-date technical information, be sure to visit us online at www.LayfieldGroup.com